

weberset one fix

C2E Tile Adhesive for Large Porcelain Tiles on Floor



weberset one fix is a single-component, water-resistant, cement-based, ultra-thick bed adhesive. It is classified as a C2E adhesive with high strength and extended open time. Suitable for 6-15 mm bed thickness.

PRODUCT BENEFITS



ECO FRIENDLY



HIGH STRENGTH



APPLICATION DEPTH

USAGE

Ideal for fixing a wide range of large format tiles and stones, including ceramic, porcelain, vitrified, mosaics, natural stones, brick veneer, and decorative stones, on walls and floors in dry or wet, interior or exterior environments. It is not suitable for skim-coated plaster, painted, or metal surfaces. Suitable substrates include well-cured concrete (minimum 6 weeks), cement-sand render and screed (cured 2-3 weeks), existing tiles or stone surfaces (dry, sound, contaminant-free), vinyl tiles (primed), rigid building boards (primed), and strong timber floors overlaid with marine plywood.

TECHNICAL DATA & PHYSICAL PROPERTIES

Colour	Grey
Density	Approx. 1.6 g/m ³
pH	12
Dry Solid Content	100 %
Bed Thickness	6-15 mm
Water Demand	Approx. 20-24 % or 5-6 litres/25 kg bag
Adjustability Time	Approx. 25 minutes
Working Time (Pot Life)	Approx. 2 hours
Open Time @ 30°C (ISO 13007-2 Clause 4.1)	Approx. 30 minutes
Setting Time	Approx. 4-6 hours (Initial); Approx. 14 hours (Final)
Application Temperature	5-40 °C
Temperature Resistance	100 °C
Frost Resistance	-15 °C
Resistance to Acids	Fair
Resistance to Alkalis	Good
Resistance to Oil & Solvents	Fair
Damp Resistance	Good
Tensile Adhesion Strength (EN ISO 13007-2 Clause 4.4)	1.4-1.7 N/mm ² (After 28 days air cure) 1.1-1.3 N/mm ² (After water immersion) 1.1-1.3 N/mm ² (After heat aging)
Classification under (ISO 13007-1)	C2E Adhesive

Specifications are subject to change without notification. Results shown are typical but reflect laboratory test procedures conducted in laboratory conditions. Actual field performance will depend on installation methods and site conditions.

CONSUMPTION

Approx. 6 kg/m² at 6 mm bed thickness or approx. 15 kg/m² at 15 mm bed thickness.

SAINT-GOBAIN WEBER (M) SDN BHD

No 29 & 31, Jalan TIAJ 2/1, Taman Industri Alam Jaya, 42300 Bandar Puncak Alam, Selangor D E, Malaysia

(603) 60389498/97/89 (603) 6038 9507 info.webermalaysia@saint-gobain.com www.saint-gobain.my



weberset one fix

C2E Tile Adhesive for Large Porcelain Tiles on Floor

PROCEDURE & APPLICATION



Substrate Preparation

All surfaces must be clean, sound, and free from any laitance, oil, grease, and any contaminants. Ceramic tiles are to be fixed dry. Do not soak in water.



Mixing

Mix weberset one fix with the required amount of clean water or latex admixture (webermix admix 1, webermix admix plus or webermix multibond). weberset one fix requires mixing with water unless special conditions where latex admixture can be used in replacement of water, to enhance physical properties. Mechanical mixing is recommended.



Application

Spread weberset one fix with a suitable notched trowel. Spread no more than 1 m² at a time to avoid skin-over. Fix tiles onto the adhesive bed, followed by a slight twisting action to secure contact. Touch the adhesive bed periodically to check for skin-over. Adjustability time varies and is approx. 25 minutes. Allocate joints of approx. 2-3 mm wide between tiles. Remove surplus adhesive from tile surface and joints before it hardens. The adhesive should not be used in temperatures lower than 5°C or in damp conditions.



Grouting

Grouting of tile joints should only commence at least 24 hours after completion of tiling or until the adhesive has set. Setting may be delayed on dense or impervious surfaces. Use weberfill fine grout or weberfill f&w grout and etc. depending on grouting joints widths and specific areas requirement.



Movement Joints (BS 5385: Part 1-5)

- Over existing structural joints.
- Where tiling abuts other materials.
- At junctions between different background materials.
- In large areas of floor or wall tiling, at 3-4.5 m centres vertically & horizontally and the floor perimeter or corners.
- Around a fix structure i.e., column or machinery.
- Where stresses are concentrated i.e., changes in the wall or floor alignment.

STORAGE & PACKING

weberset one fix is available in 25 kg bags.

Shelf life of 12 months if unopened, and kept in sheltered and dry conditions.

HEALTH & SAFETY

weberset one fix contains cement, which may produce an allergic effect. Material may irritate eyes and skin. In case of contact with eyes, rinse immediately with plenty of water, and seek medical assistance. After contact with the skin, wash immediately with plenty of soap and water. Please keep out of reach of children.

*Note Because it is not possible to give specific instructions for the various site conditions or to control the applications, the information on this Technical Data Sheet is for general guidance only. Saint-Gobain Weber (M) Sdn Bhd reserves the rights to amend the contents of the data sheet at its sole discretion. (Sep '25)



SAINT-GOBAIN WEBER (M) SDN BHD

No 29 & 31, Jalan TIAJ 2/1, Taman Industri Alam Jaya, 42300 Bandar Puncak Alam, Selangor D E, Malaysia

(603) 60389498/97/89 (603) 6038 9507 info.webermalaysia@saint-gobain.com www.saint-gobain.my

